



Waterloo Road, London NW2 7TX. Tel: +44 (0)20 8450 4666 www.bondaglass.com

June 2018

PRODUCT DATA SHEET

Product	Bondaflex PU
Type	High viscosity moisture-curing polyurethane sealant.
Intended Use	Use for rapid bonding of wood to wood. Can also be used to bond rigid and flexible facing materials as used for structural sandwich panels and insulated building boards, i.e. for cold stores, mobile homes/offices etc.
Special Features	Solvent-free single pack sealant that is non-toxic to fish once fully cured.
Preparation	Ensure surfaces are clean, dry and free of loose material.
Application	Apply sealant using the bottle applicator to a clean and dry substrate.
Coats	One application.
Drying Time	Fixture time 5 - 10 minutes. Full cure in 24 hours.
Re-coating Time	Not applicable.
Application Temp.	Working range; +5 to +30°C.
Coverage	Depending on porosity and smoothness of surface and application, 80 – 140 grams per sq. m.
Maintenance	Not applicable.
Compatibility	Suitable for use with brick, stone, metal, most plastics, PVC and rubber pond liners.
Settlement	Not applicable.
Shelf-life/Storage	Minimum 12 months when stored in a cool, dry place out of direct sunlight in the original, sealed container. Do not store below +5°C.
Hazards	Contains di-isocyanates. Harmful by inhalation. Irritant. Avoid eye and skin contact as this product will bond surfaces together. In case of skin or eye contact wash copiously with water. Wear suitable protective glasses and gloves. Keep away from children. Health and Safety Data Sheet available on request or from website.
Clean-Up	Use warm soap water while uncured.
Sizes	310ml