

Hotspot Ltd, Waterloo Road, London NW2 7TX. Tel: +44 (0)20 8450 4666 www.rustins.ltd/hotspot

November 2020

PRODUCT DATA SHEET

Product	Grate Paint (Silk Finish)
Туре	A high temperature, corrosion resistant, decorative finish.
Intended Use	Formulated for use on cast iron and steel.
Special Features	Protective as well as decorative.
Preparation	Ensure the surface to be treated is cool and any heat source is extinguished. Remove all rust, scale, dirt, grease and check that the surface is dry.
Application	Apply by brush or spray. Agitate paint until well mixed. Recommended thickness of 22 microns ± 3 microns, in practice this means apply in thin coats, allowing to fully dry before applying the next coat. Building up layers this way gives maximum high temperature resistance. Optimum corrosion and abrasion resistance may be achieved by oven-curing although curing will take place during operation of the product or components. A thin coating allows excellent heat transmission and is colour fast for up to 350°C, when allowed to cool for up to 24 hours.
Coats	Two coats recommended.
Drying Time	Touch dry in 2-3 hours at room temperature. Oven cured at 20 minutes at 250°C – adequate ventilation should be provided at all stages of the curing operation.
Re-coating Time	2-3 hours.
Application Temp.	Cool for application, 250 deg. C for curation.
Coverage	Approximately 7m ² /Litre at 20 microns.
Maintenance	As required.
Compatibility	Most substrates including steel and its alloys can be coated successfully; however, we recommend that each new substrate should be checked for its suitability.
Settlement	Shake well before use.
Shelf-life/Storage	2 years if stored unopened in a cool, dry place.
Hazards	Extremely flammable; harmful; harmful by inhalation and in contact with skin and eyes. Keep out of reach of children.
Clean-Up	Clean with xylene thinners.
Sizes	450ml aerosols.